



UNLIMITED CREATION

APPLICATION INSTRUCTIONS

FantasyFlex

Bright colors and beautiful patterns will transport your graphics into a Fantasy world.
FantasyFlex is 100%PU, cuts and weeds very easily.

FEATURES:



printed
PU



80µ



Cotton, polyester,
blended fabrics..
Less suitable for nylon
and other coated textiles.



40°C

CUTTING CONDITIONS:



Blade
30 - 45°



low/
medium



30 - 40 cm/s

TRANSFER CONDITIONS:



165°C



17 s



medium/
high



Hot peel

► PACKAGING



49 cm


25 m

49 cm


10 m

49 cm

5 m



1. Cut mirrored



2. Weed design



3. Transfer design



4. Remove liner, done !

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 12 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

SEF • 110 BD DENIS-PAPIN 53000 LAVAL – FRANCE
TEL. +33 2. 43 53 36 48 FAX +33 2. 43 67 11 78
www.seftextile.com E-mail: contact@sef-france.com
SAS. CAPITAL € 945 000 RCS, LAVAL 304.802.291.00027



AVAILABLE COLORS


FantasyFlex




GRAFF 01



CAMO 02




KALEIDOSCOPE 03




BLUE SNAKE 04



FLOWERS 05



MAZE 06



BARCELONA 07




BAYADERE 08



FABRIC 09



ZEBRA 10



MARBLE 11



MORNING CLOUD 12

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 12 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.