



# UNLIMITED CREATION

## APPLICATION INSTRUCTIONS

# FlexCut Atomic



7 new sparkly colours for your brilliant designs.

100% Polyurethane film, high durability and the trusted FlexCut easy cutting & weeding.

### FEATURES:



**PU water-based**



**60µ**



**Cotton, polyester, blended fabrics..**  
Less suitable for nylon and other coated textiles.



**60°C**

### CUTTING CONDITIONS:



**Blade 30 - 45°**



**low/medium**



**30 - 40 cm/s**

### TRANSFER CONDITIONS:



**165°C**



**17 s**




**medium/high**




**Hot peel**

**Flex on Flex possible**



**1. Cut mirrored**



**2. Weed design**



**3. Transfer design**



**4. Remove liner, done !**

### ► PACKAGING



50 cm

25 m

50 cm

10 m

50 cm

5 m

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 18 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

**SEF • 110 BD DENIS-PAPIN 53000 LAVAL – FRANCE**  
**TEL. +33 2. 43 53 36 48      FAX +33 2. 43 67 11 78**  
**www.seftextile.com E-mail: contact@sef-france.com**  
**SAS. CAPITAL € 945 000 RCS, LAVAL 304.802.291.00027**





# UNLIMITED CREATION

## AVAILABLE COLORS

# FlexCut Atomic



**ORANGE A03**  
P 8945 C




**RED A02**  
~ P 10165 C



**PINK A01**  
P 10167 C




**PURPLE A06**  
P 8140 C



**CHERRY A07**  
P 10177 C



**BLUE A05**  
P 10261 C



**GREEN A04**  
~P 10439 C

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 18 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

**S E F • 110 BD DENIS-PAPIN 53000 LAVAL – FRANCE**  
**TEL. +33 2. 43 53 36 48      FAX +33 2. 43 67 11 78**  
**www.seftextile.com E-mail: [contact@sef-france.com](mailto:contact@sef-france.com)**  
**SAS. CAPITAL € 945 000 RCS, LAVAL 304.802.291.00027**

