



UNLIMITED CREATION

APPLICATION INSTRUCTIONS

FlexCut Sweet

FlexCut Sweet is a "screen printing like" 100 polyurethane heat transfer film - very stretchable and incredibly soft.

FEATURES:



**PU
water-
based**



60µ



**Cotton, polyester,
blended fabrics..**
Less suitable for nylon
and other coated textiles.



60°C

CUTTING CONDITIONS:



**Blade
30 - 45°**



**low/
medium**



30 - 40 cm/s

TRANSFER CONDITIONS:



165°C



17 s



**medium/
high**



Cold peel

Flex on Flex possible

► PACKAGING



50 cm


25 m

50 cm


10 m

50 cm

5 m



1. Cut mirrored



2. Weed design



3. Transfer design



4. Remove liner, done !

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 24 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

S E F • 110 BD DENIS-PAPIN 53000 LAVAL – FRANCE
TEL. +33 2. 43 53 36 48 FAX +33 2. 43 67 11 78
www.seftextile.com E-mail: contact@sef-france.com
SAS. CAPITAL € 945 000 RCS, LAVAL 304.802.291.00027





UNLIMITED CREATION

AVAILABLE COLORS

FlexCut Sweet



WHITE 01



PACIFIC BLUE 19

P 647 C



GOLD METALLIC 32

P 871 C



LEMON YELLOW 05

P 012 C



ROYAL BLUE 21

P 280 C




SILVER METALLIC 31

P 877 C



SUNNY YELLOW 06

P 116 C



NAVY BLUE 22

P 289 C



ORANGE 07

P 021 C



GREEN 25

P 341 C



ELECTRIC RED 12

P 1797 C



COOL GREY 14

P COOL GRAY 8 C



RED 10

P 1945 C



BLACK 02

P PROCESS BLACK C

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 24 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

S E F • 110 BD DENIS-PAPIN 53000 LAVAL – FRANCE
TEL. +33 2. 43 53 36 48 FAX +33 2. 43 67 11 78
www.seftextile.com E-mail: contact@sef-france.com
SAS. CAPITAL € 945 000 RCS, LAVAL 304.802.291.00027



Modifié 05/2020