



UNLIMITED CREATION

APPLICATION INSTRUCTIONS

RocketCut

RocketCut - the Swiss army knife of heat transfer films!

Very fast weeding, 3s transfer time, suitable for many textiles where standard flex doesn't work and even with a slight migration barrier.

FEATURES:



**PU
water-
based**



70µ



**Cotton, polyester,
blended fabrics..**
Also suitable for many
water repellent coated textiles.



60°C

CUTTING CONDITIONS:



**Blade
30 - 45°**



**low/
medium**



30 - 40 cm/s

TRANSFER CONDITIONS:



**150 °C
125 °C**



**3 s
10 s**



**medium/
high**



Hot peel

► PACKAGING



50 cm


25 m

50 cm

10 m

50 cm

5 m



1. Cut mirrored



2. Weed design



3. Transfer design



4. Remove liner, done !

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 12 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

S E F • 110 BD DENIS-PAPIN 53000 LAVAL – FRANCE
TEL. +33 2. 43 53 36 48 FAX +33 2. 43 67 11 78
www.seftextile.com E-mail: contact@sef-france.com
SAS. CAPITAL € 945 000 RCS, LAVAL 304.802.291.00027



AVAILABLE COLORS

RocketCut

| | | | | | | | |
|--|------------------------------------|---|-------------------------------------|---|-------------------------------------|---|---|
|  | WHITE 01 P 000 C |  | FUCHSIA 09 P 205 C |  | ROYAL BLUE 21 P 280 C |  | COOL GREY 14 P COOL GRAY 8 C |
|  | DENT-DE-LION 47 P 1215 C |  | BURGUNDY 13 P 7428 C |  | NAVY BLUE 22 P 289 C |  | GREY 15 P 430 C |
|  | LEMON YELLOW 05 P 012 C |  | LAVANDER BLUE 46 P 2706 C |  | MINT GREEN 44 P 573 C |  | DARK GREY 16 P COOL GRAY 11 C |
|  | SUNNY YELLOW 06 P 116 C |  | MOONBERRY 49 P 680 C |  | TURQUOISE 34 P 3125 C |  | BLACK 02 P PROCESS BLACK C |
|  | SODA ORANGE 48 P 162 C |  | LAVANDER 37 P 2772 C |  | VIBRANT GREEN 35 P 375 C |  | NEON YELLOW 39 P 809 C |
|  | ORANGE 07 P 021 C |  | PLUM 38 P 259 C |  | APPLE GREEN 24 P 376 C |  | NEON ORANGE 40 P 811 C |
|  | FIRE RED 11 P 1795 C |  | PURPLE 23 P VIOLET C |  | LIGHT GREEN 36 P 347 C |  | NEON PINK 41 P 812 C |
|  | PASSION RED 33 P 185 C |  | SKY BLUE 17 P 418 C |  | GREEN 25 P 341 C |  | NEON GREEN 42 P 802 C |
|  | ELECTRIC RED 12 P 1797 C |  | HAWAI BLUE 50 P 7695 C |  | MILITARY GREEN 26 P 418 C |  | SILVER METALLIC 31 P 877 C |
|  | RED 10 P 1945 C |  | ATOLL BLUE 18 P 299 C |  | BEIGE 03 P 7401 C |  | GOLD METALLIC 32 P 871 C |
|  | BABY PINK 08 P 189 C |  | PACIFIC BLUE 19 P 647 C |  | DUNE 45 P 4675 C | | |
|  | CANDY PINK 43 P 508 C |  | REFLEX BLUE 20 P 072 C |  | CHOCOLATE 04 P 7519 C | | |

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 12 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.