



# UNLIMITED CREATION

## APPLICATION INSTRUCTIONS

# VelCut Touch

With VelCut Touch cutting and weeding intricate graphics is really easy! It cuts and weeds like a flex but VelCut Touch super soft feel surface is unique.

An innovative soft velour film that performs like a flex.

### FEATURES:



Microfiber flock



300µ



Cotton, polyester, blended fabrics..  
Less suitable for nylon and other coated textiles.



60°C

### CUTTING CONDITIONS:



Blade 30 - 45°



low/medium



30 - 40 cm/s

### TRANSFER CONDITIONS:



160 - 170 °C



17 - 15 s



low/medium



Warm peel

Flex on Flex possible

### ► PACKAGING



50 cm

25 m

50 cm


10 m

50 cm

5 m



1. Cut mirrored



2. Weed design



3. Transfer design



4. Remove liner, done !

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 36 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

SEF • 110 BD DENIS-PAPIN 53000 LAVAL – FRANCE  
TEL. +33 2. 43 53 36 48 FAX +33 2. 43 67 11 78  
www.seftextile.com E-mail: contact@sef-france.com  
SAS. CAPITAL € 945 000 RCS, LAVAL 304.802.291.00027





# UNLIMITED CREATION

## AVAILABLE COLORS

# VelCut Touch



WHITE 91



ORANGE 82

P 021 U



PACIFIC BLUE 98

P 300 U



LIGHT GREY 89

P COOL GRAY 8 C



LEMON 92

P 109 C



ELECTRIC RED 94

P 186 C



ROYAL BLUE 99

P 280 C



COOL GREY 81

P COOL GRAY 9 C



YELLOW 93

P 2010 C



RED 95

P 192 C



NAVY BLUE 97

P 533 C



BLACK 96

P HEXACHROME BLACK C

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 36 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

**S E F • 110 BD DENIS-PAPIN 53000 LAVAL – FRANCE**  
**TEL. +33 2. 43 53 36 48      FAX +33 2. 43 67 11 78**  
**www.seftextile.com E-mail: contact@sef-france.com**  
**SAS. CAPITAL € 945 000 RCS, LAVAL 304.802.291.00027**

